

PENETRATION BITUMEN 60/70

	SPECIFICATION	TEHST METHOD
Specific Gravity @25/25°C	1.01/1.06	D-70
Penetration @ 25°C	60/70	D-5
Softening Points °C	49/56	D-36
Ductility @ 25°C	100 min.	D-113
Loss on Heating (wt)%	0.2 max.	D-6
Drop in Penetration after Heating %	20 max.	D-6&D-5
Flash Point °C	250 min.	D-92
Solubility in CS ₂ (wt)%	99.5 min.	D-4
Spot Test	Negative	*A.A.S.H.O.T.10 2

Origin: Iran

PENETRATION BITUMEN 85/100

	SPECIFICATIO N	TEHST METHOD
Specific Gravity @25/25°C	1.01/1.05	D-70
Penetration @ 25°C	85/100	D-5
Softening Points °C	45/52	D-36
Ductility @ 25°C	100 min.	D-113
Loss on Heating (wt)%	0.5 max.	D-6
Drop in Penetration after Heating %	20 max.	D-6&D-5
Flash Point °C	225 min.	D-92
Solubility in CS ₂ (wt)%	99.5 min.	D-4
Organic Matter Insoluble in CS ₂ (wt)%	0.2 max.	D-4
Spot Test	Negative	*A.A.S.H.O.T.1 02

Origin: Iran