

PENETRATION BITUMEN 60/70

| PROPERTY | SPECIFICATION | TEST METHOD |
|-------------------------------------|----------------------|----------------------|
| Specific Gravity @25/25°C | 1.01/1.06 | D-70 |
| Penetration @ 25°C | 60/70 | D-5 |
| Softening Points °C | 49/56 | D-36 |
| Ductility @ 25°C | 100 min. | D-113 |
| Loss on Heating (wt)% | 0.2 max. | D-6 |
| Drop in Penetration after Heating | 20 max. | D-6&D-5 |
| Flash Point °C | 250 min. | D-92 |
| Solubility in CS ₂ (wt)% | 99.5 min. | D-4 |
| Spot Test | Negative | *A.A.S.H.O.T.10 2 |

Origin: Iran

PENETRATION BITUMEN 85/100

| PROPERTY | SPECIFICATION | TEST METHOD |
|---|----------------------|----------------------|
| Specific Gravity @25/25°C | 1.01/1.05 | D-70 |
| Penetration @ 25°C | 85/100 | D-5 |
| Softening Points °C | 45/52 | D-36 |
| Ductility @ 25°C | 100 min. | D-113 |
| Loss on Heating (wt)% | 0.5 max. | D-6 |
| Drop in Penetration after Heating | 20 max. | D-6&D-5 |
| Flash Point °C | 225 min. | D-92 |
| Solubility in CS ₂ (wt)% | 99.5 min. | D-4 |
| Organic Matter Insoluble in CS ₂ (wt)% | 0.2 max. | D-4 |
| Spot Test | Negative | *A.A.S.H.O.T.1 02 |

Origin: Iran