

PARAFFIN WAX SPECIFICATION

NO.	CHARACTERSTIC	RESULT	METHOD
1.	Color (Lovibond)	0.3 Y-0.5 Y	IP-17 Method (2"cell)
2.	Congeaing point	62-68 C	ASTM D-938
3.	Melting point	60-65 C	ASTM D-87
4.	Oil content	3-5%	ASTM D-721
5.	Kinematics' viscosity @ 100 C	6-7.5 cst	ASTM D-445
6.	Density @ 100 C	0.760- 770gr/cm ³	ASTM D-1298
7.	Flash point	MIN 230 C	ASTM D-92

Packing: 5 slabs per carton (PST Slab 50cm* 30cm* 5cm*)

Origin: Iran